



Technical Data Sheet

FLOPAM™ AN 923 SEP

Appearance	White powder	
Ionic character	Anionic	
Charge density	Medium	
Molecular weight	Very high	
Mesh size	% > 10 mesh :	2
	% < 100 mesh :	6
Approx. bulk density	0.80	
Brookfield viscosity (cps)^{††}	@ 5.0 g/l	1395
	@ 2.5 g/l	525
	@ 1.0 g/l	180
Recommended working concentration (g/l)	3	
Maximum concentration (g/l)	5	
Dissolution time (minutes) in DI water @ 5 g/l, 25°C	90	
Stability of D.I. solution (days)	1	
Storage temperature (°C)	0 - 35	
Shelf life (months) *	24	

†† Average values given for determination of preparation and dosing equipment for which a viscosity 10 times lower can be used.

* When stored inside a building at a stable temperature between 5° and 30°C.

Packing sizes

Multiwall bags	25 kg
Big bags	500 & 750 kg
Other dimensions	On request

The data in this Technical Data Sheet is provided for information only. It is correct to the best of our knowledge, information and belief at the date of its publication. It does not constitute a specification and no liability is assumed, nor freedom from any existing patents.